

Synthesis and Characterization of 1-(2-Hydroxyethyl)-3-Methyl Imidazolium and N-(2-Hydroxyethyl)-N-Methyl Morpholinium Ionic Liquids

S. Choi,^S K.S. Kim, J.H. Cha, S.H. Yoen, and H. Lee^C

*Department of Chemical and Biomolecular Engineering, Korea Advanced Institute of Science and Technology,
Yuseong-gu, Daejeon, Korea
h_lee@kaist.ac.kr*

In this study, various ionic liquids (ILs) were prepared, via metathesis reactions, from two kinds of cations: 1-(2-hydroxyethyl)-3-methyl imidazolium ([HEMIm]⁺) and N-(2-hydroxyethyl)-N-methyl morpholinium ([HEMMor]⁺), and three kinds of anions: tetrafluoroborate ([BF₄]⁻), bis(trifluoromethanesulfonyl)imide ([TFSI]⁻), and hexafluorophosphate ([PF₆]⁻). All of the [HEMIm]⁺ derivatives were in a liquid state at room temperature. In particular, both [HEMIm][BF₄] and [HEMIm][TFSI] showed no possible melting point from -150 to 200 °C by DSC analysis, and their high thermal stability until 380 ~ 400 °C was verified by TGA analysis. Also, their stable electrochemical properties (electrochemical windows of more than 6.0 V) and high ionic conductivities (0.002 to 0.004 S·cm⁻¹) further confirm that the suggested ILs are electrolytes potentially usable in electrochemical devices. Simultaneously, the [HEMMor]⁺ derivatives have practical value in electrolyte applications because of their easy synthesis procedures, cheap morpholinium cation sources, and the possibility of high Li⁺ mobility because of the oxygen group in the morpholinium cation. However, [HEMMor]⁺ derivatives with high viscosities usually had lower ionic conductivities than [HEMIm]⁺ derivatives.